CHITOSAN FLOWCHART

Chitin 甲壳素 → Resolve into 1% HCL solution 溶解1%盐酸 → Complete dissolve 完全溶解

→ Add 31% HCL 加 31%的盐酸 → Heat to 100 ℃ 加热到 100 度 → Keep the temperature according to various specs 根据粘度要求保温

→ Neutralize with NaOH Solution (5%～7%)用5-7%碱中和 → Deacetylated by NaOH (90-95%)用90-95%碱乙酰化 → Immerse into ethanol 用乙醇洗涤

→ Dryness 干燥 → Smashing 粉碎 → Packing 保证

→ Chitosan 壳聚糖

中国江苏高邮同心路 2 号 邮编 225601 电话:0086-514-84549155 传真 0086-514-84549297
No2TongxinRD,GaoyouCity,Jiangsu,China PO.225601 TEL:0086-514-84549155 FAX:0086-514-84549297
http://www.rxgp.com email:jsrx@gaoyou.com